






TECHNICAL DATA SHEET

Z-Grip®
Super Lightweight Filler

101667
104167

| | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|------------------------------------|--|-------|-------|----------------|--------|-------------|---------------------------|------------------|------|----------------|--------------|-----------------------|----------------------------|------------|---|--------|--------------------|----------|-------------|------------------|------------|-----------|------------------------|------------------|------------------------|------------------------------------|------------------------------------|
| DESCRIPTION: | This heavy filling, smooth spreading, easy leveling, and easy sanding filler offers excellent featheredge adhesion to bare steel, galvanized and other zinc coated steel, SMC, fiberglass and aluminum. It can also be used for cosmetic fiberglass and composite repairs. The Non-Clog formulas adds greater value in sandpaper savings. | | | | | | | | | | | | | | | | | | | | | | | | | | |
| USES: | FOR PROFESSIONAL USE ONLY A super-lightweight body filler formulated for superior adhesion. Extremely easy to sand with little resistance. | | | | | | | | | | | | | | | | | | | | | | | | | | |
| STORAGE: |  <p>Store in accordance with local regulations. Observe label precautions. Do not store above the following temperature: 25°C (77°F). Store in a cool, well-ventilated area away from incompatible materials and ignition sources. Keep away from: oxidising agents, strong alkalis, strong acids. No smoking. Prevent unauthorised access. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not empty into drains. Never return mixed product back into container.</p> | | | | | | | | | | | | | | | | | | | | | | | | | | |
| PREPARATION: |  <p>Prior to sanding, clean the entire repair area with soap and water, followed by a mild degreasing cleaning solvent. Sand repair area, removing only the paint. Use finer grit to remove any coarse sand scratches and to featheredge the paint. Remove dust.</p> | | | | | | | | | | | | | | | | | | | | | | | | | | |
| MIXING: |  <p><i>Use with Cream Hardener Only!</i> Measure hardener 2% by weight (approximately a ribbon of cream hardener from edge to edge across the center of a 10cm diameter puddle). Puddles larger than 10cm in diameter will require additional hardener. Mix thoroughly until uniform color is achieved.</p> | | | | | | | | | | | | | | | | | | | | | | | | | | |
| APPLICATION: |  <p>Apply in thin layers and spread smoothly. Allow to cure fully before finishing.</p> | | | | | | | | | | | | | | | | | | | | | | | | | | |
| FINISHING: |  <p>Sand to knock down high spots. Avoid coarse sand scratches outside the repair area during the initial cut. Finish sand and featheredge to remove scratches.</p> | | | | | | | | | | | | | | | | | | | | | | | | | | |
| TECHNICAL SPECIFICATIONS: | <table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td>Color</td> <td>Green</td> </tr> <tr> <td>Physical state</td> <td>Liquid</td> </tr> <tr> <td>Flash Point</td> <td>Open cup: 37.5°C (99.5°F)</td> </tr> <tr> <td>Relative Density</td> <td>1.04</td> </tr> <tr> <td>Vapour Density</td> <td>>1 [Air = 1]</td> </tr> <tr> <td>Lower explosion limit</td> <td>Lower: 1.1% Upper: 6.1%</td> </tr> <tr> <td>Solubility</td> <td>Insoluble in the following materials: cold water and hot water.</td> </tr> <tr> <td>Weight</td> <td>1042.5 g/L average</td> </tr> <tr> <td>Pot Life</td> <td>3-5 minutes</td> </tr> <tr> <td>Dry to Sand Time</td> <td>20 minutes</td> </tr> <tr> <td>Viscosity</td> <td>220,000 to 270,000 cps</td> </tr> <tr> <td>Shore D Hardness</td> <td>65 to 70 (24 hr. cure)</td> </tr> <tr> <td>Lap Shear Adhesion at 20/40/60 min</td> <td>1000 psi (minimum on sanded steel)</td> </tr> </table> | Color | Green | Physical state | Liquid | Flash Point | Open cup: 37.5°C (99.5°F) | Relative Density | 1.04 | Vapour Density | >1 [Air = 1] | Lower explosion limit | Lower: 1.1% Upper: 6.1% | Solubility | Insoluble in the following materials: cold water and hot water. | Weight | 1042.5 g/L average | Pot Life | 3-5 minutes | Dry to Sand Time | 20 minutes | Viscosity | 220,000 to 270,000 cps | Shore D Hardness | 65 to 70 (24 hr. cure) | Lap Shear Adhesion at 20/40/60 min | 1000 psi (minimum on sanded steel) |
| Color | Green | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Physical state | Liquid | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Flash Point | Open cup: 37.5°C (99.5°F) | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Relative Density | 1.04 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Vapour Density | >1 [Air = 1] | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Lower explosion limit | Lower: 1.1% Upper: 6.1% | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Solubility | Insoluble in the following materials: cold water and hot water. | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Weight | 1042.5 g/L average | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Pot Life | 3-5 minutes | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Dry to Sand Time | 20 minutes | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Viscosity | 220,000 to 270,000 cps | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Shore D Hardness | 65 to 70 (24 hr. cure) | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Lap Shear Adhesion at 20/40/60 min | 1000 psi (minimum on sanded steel) | | | | | | | | | | | | | | | | | | | | | | | | | | |

TECHNICAL DATA SHEET

Z-Grip®
Super Lightweight Filler

101667
104167

| | |
|-------------------------------|---|
| | <p>Corrosion Resistance 500 hours Harsaw salt Spray Cabinet 300 hours at 100% RH</p> <p>Water Resistance No blistering, wrinkling or softening after 24 hours immersion in water.</p> <p>Max. recommended Thickness (sanded) 6.3 mm</p> <p>Contents and Caution MSDS Available upon request</p> <p>VOC 2004/42/IIIB(b)(250)(95) IIB/b. Bodyfiller/stopper – All types. EU limit values: 250g/l. (2007) This product contains a maximum of 95 g/l VOC.</p> <p>Properties are typical values and should not be considered as sales specifications. Physical testing performed at approximately 25°C (77°F)/ 75% RH unless otherwise noted.</p> |
| SAFETY & HANDLING: | Read all directions and warnings prior to using Evercoat products. Material Safety Data Sheets can be found online at evercoat.com. |