

EVERCOAT®

EVERCOAT®

NEW

SUPER BUILD 4:1

ULTRA HIGH BUILD POLYESTER PRIMER SURFACER

TWICE THE FILM BUILD OF OTHER POLYESTER PRIMERS!

- Direct to Metal application eliminates the need for epoxy or self-etch primers
- Easy, accurate mixing without a scale
- Sprays with less overspray than traditional polyester primers



Part No.
100733



Part No.
100730

EVERCOAT®

SUPER BUILD 4:1

ULTRA HIGH BUILD POLYESTER PRIMER SURFACER

MIXING:



- Shake and stir thoroughly before mixing.
- Mix thoroughly before pouring primer into gun cup
- Pot life is 60 minutes @ 75°F (24°C); pot life decreases at higher temperatures
- Do not leave product in the spray gun for longer than 45 minutes

APPLICATION:

- Use a primer gun with a 1.6 to 2.2 fluid nozzle/air cap
- Adjust air pressure to 40-45psi for conventional guns or 10 psi at the cap for HVLP
- Apply 2 – 3 medium wet coats allowing 5 – 10 minutes flash time between coats

FINISH:

- Super Build 4:1 is ready to sand in about 2 hours, depending on film build
 - Force Dry – Bake 30 minutes @ 140°F (60°C)
- Once dry, sand Super Build 4:1 with 180-400 grit sandpaper prior to next step

TECHNICAL

DATA:

Appearance	Gray liquid
VOC	Packaged: 2.02 lbs/gal (243g/L) Applied: 1.51 lbs/gal (180.9g/L)
Wet-Film-Thickness (WFT)	8.0 - 10.0 mils per coat
Dry-Film-Thickness (DFT)	6.0 – 8.0 mils per coat
Solids by Volume	65 – 70%
Solids by weight	70 – 75%
Viscosity (ready to spray)	30 – 35 seconds in Zahn #3
Coverage at 1 mil 100% Transfer	1200 sq. ft. per US gallon

EVERCOAT®

Evercoat | a division of Illinois Tool Works Inc. | 6600 Cornell Road | Cincinnati, OH 45242 | (513) 489-7600
Made and Printed in the U.S. | ©2010 Evercoat

evercoat.com

704165 (3/10)