






TECHNICAL DATA SHEET

EuroSand™
Filler

103274

USES:	<p>FOR PROFESSIONAL USE ONLY</p> <p>Euro Sand is a hybrid filler putty. It is thick enough for heavy filling, yet smooth and creamy. Euro Sand can also be used for skim coating bodywork, pinholes, grind marks, low spots and other surface imperfections. Euro Sand has excellent hang and superior adhesion.</p>																										
STORAGE:	 <p>Store in accordance with local regulations. Observe label precautions. Do not store above the following temperature: 25°C (77°F). Store in a cool, well-ventilated area away from incompatible materials and ignition sources. Keep away from: oxidizing agents, strong alkalis, and strong acids. No smoking. Prevent unauthorized access. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not empty into drains. Never return mixed product back into container.</p>																										
PREPARATION:	 <p>Prior to sanding, clean the entire repair area with soap and water, followed by a mild degreasing cleaning solvent. Sand repair area, removing only the paint. Use finer grit to remove any coarse sand scratches and to featheredge the paint. Remove dust.</p>																										
MIXING:	 <p><i>Use with Cream Hardener Only!</i></p> <p>Measure hardener 2% by weight (approximately a ribbon of cream hardener from edge to edge across the center of a 10cm diameter puddle). Puddles larger than 10cm in diameter will require additional hardener. Mix thoroughly until uniform color is achieved.</p>																										
APPLICATION:	 <p>Apply in thin layers and spread smoothly. Do not apply over fresh or uncured coatings. Allow to cure fully before finishing.</p>																										
FINISHING:	 <p>Sand to knock down high spots. Avoid coarse sand scratches outside the repair area during the initial cut. Finish sand and featheredge to remove scratches.</p>																										
TECHNICAL SPECIFICATIONS:	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td>Color</td> <td>White</td> </tr> <tr> <td>Flash Point</td> <td>Open cup: 35°C (95°F)</td> </tr> <tr> <td>Relative Density</td> <td>1.13</td> </tr> <tr> <td>Vapor Density</td> <td>>1 [Air = 1]</td> </tr> <tr> <td>Lower explosion limit</td> <td>Lower: 1.1% Upper: 6.1%</td> </tr> <tr> <td>Solubility</td> <td>Insoluble in the following materials: cold water and hot water.</td> </tr> <tr> <td>Weight</td> <td>1130 g/L average</td> </tr> <tr> <td>Pot Life</td> <td>4-6 minutes</td> </tr> <tr> <td>Dry to Sand Time</td> <td>20 minutes</td> </tr> <tr> <td>Viscosity</td> <td>150,000-200,000 cps</td> </tr> <tr> <td>Shore D Hardness</td> <td>65 to 70 (24 hr. cure)</td> </tr> <tr> <td>Max. recommended Thickness (sanded)</td> <td>3 mm</td> </tr> <tr> <td>Contents and Caution</td> <td>MSDS Available upon request</td> </tr> </table>	Color	White	Flash Point	Open cup: 35°C (95°F)	Relative Density	1.13	Vapor Density	>1 [Air = 1]	Lower explosion limit	Lower: 1.1% Upper: 6.1%	Solubility	Insoluble in the following materials: cold water and hot water.	Weight	1130 g/L average	Pot Life	4-6 minutes	Dry to Sand Time	20 minutes	Viscosity	150,000-200,000 cps	Shore D Hardness	65 to 70 (24 hr. cure)	Max. recommended Thickness (sanded)	3 mm	Contents and Caution	MSDS Available upon request
Color	White																										
Flash Point	Open cup: 35°C (95°F)																										
Relative Density	1.13																										
Vapor Density	>1 [Air = 1]																										
Lower explosion limit	Lower: 1.1% Upper: 6.1%																										
Solubility	Insoluble in the following materials: cold water and hot water.																										
Weight	1130 g/L average																										
Pot Life	4-6 minutes																										
Dry to Sand Time	20 minutes																										
Viscosity	150,000-200,000 cps																										
Shore D Hardness	65 to 70 (24 hr. cure)																										
Max. recommended Thickness (sanded)	3 mm																										
Contents and Caution	MSDS Available upon request																										

TECHNICAL DATA SHEET

EuroSand™
Filler

103274

	<p>2004/42/IIIB(b)(250)(126) VOC IIB/b. Body filler/stopper – All types. EU limit values: 250g/l. (2007) This product contains a maximum of 126 g/l VOC.</p> <hr/> <p>Properties are typical values and should not be considered as sales specifications. Physical testing performed at approximately 25°C (77°F)/ 75% RH unless otherwise noted.</p>
SAFETY & HANDLING:	<p>Read all directions and warnings prior to using Evercoat products. Material Safety Data Sheets can be found online at evercoat.com.</p>