






TECHNICAL DATA SHEET

Easy Sand™ - Flowable

103235

Flowable Stopper

| | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|-------------------------------------|---|-------|-------|----------------|--------|-------------|-----------------------|------------------|------|----------------|--------------|-----------------------|-------------|--|-------------|------------|---|--------|--------------------|----------|-------------|------------------|---------------|-----------|------------|------------------|------------------------|-------------------------------------|------|----------------------|-----------------------------|
| USES: | <p>FOR PROFESSIONAL USE ONLY</p> <p>A flowable polyester finishing and blending putty for filling and skim coating bodywork, pinholes, grind marks, low spots, and other surface imperfections. Adheres well to steel, galvanized, other zinc coated steel, aluminum, and most rigid to semi-rigid fiberglass and thermo-set plastics.</p> | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| STORAGE: | <div style="display: flex; align-items: center;">  </div> <p>Store in accordance with local regulations. Observe label precautions. Do not store above the following temperature: 25°C (77°F). Store in a cool, well-ventilated area away from incompatible materials and ignition sources. Keep away from: oxidising agents, strong alkalis, strong acids. No smoking. Prevent unauthorised access. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not empty into drains. Never return mixed product back into container.</p> | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| PREPARATION: | <div style="display: flex; align-items: center;">  </div> <p>Prior to sanding, clean the entire repair area with soap and water, followed by a mild degreasing cleaning solvent. Sand repair area, removing only the paint. Use finer grit to remove any coarse sand scratches and to featheredge the paint. Remove dust.</p> | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| MIXING: | <div style="display: flex; align-items: center;">  </div> <p><i>Use with Cream Hardener Only!</i></p> <p>Measure hardener 2% by weight (approximately a ribbon of cream hardener from edge to edge across the center of a 10cm diameter puddle). Puddles larger than 10cm in diameter will require additional hardener. Mix thoroughly until uniform color is achieved.</p> | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| APPLICATION: | <div style="display: flex; align-items: center;">  </div> <p>Apply in thin layers and spread smoothly. Do not apply over fresh or uncured coatings. Allow to cure fully before finishing.</p> | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| FINISHING: | <div style="display: flex; align-items: center;">  </div> <p>Sand to knock down high spots. Avoid coarse sand scratches outside the repair area during the initial cut. Finish sand and featheredge to remove scratches.</p> | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| TECHNICAL SPECIFICATIONS: | <table border="1" style="width: 100%; border-collapse: collapse;"> <tr><td>Color</td><td>White</td></tr> <tr><td>Physical state</td><td>Liquid</td></tr> <tr><td>Flash Point</td><td>Open cup: 35°C (95°F)</td></tr> <tr><td>Relative Density</td><td>1.02</td></tr> <tr><td>Vapour Density</td><td>>1 [Air = 1]</td></tr> <tr><td>Lower explosion limit</td><td>Lower: 1.1%</td></tr> <tr><td></td><td>Upper: 6.1%</td></tr> <tr><td>Solubility</td><td>Insoluble in the following materials: cold water and hot water.</td></tr> <tr><td>Weight</td><td>1018.5 g/L average</td></tr> <tr><td>Pot Life</td><td>5-6 minutes</td></tr> <tr><td>Dry to Sand Time</td><td>10-15 minutes</td></tr> <tr><td>Viscosity</td><td>30,000 cps</td></tr> <tr><td>Shore D Hardness</td><td>60 to 65 (24 hr. cure)</td></tr> <tr><td>Max. recommended Thickness (sanded)</td><td>3 mm</td></tr> <tr><td>Contents and Caution</td><td>MSDS Available upon request</td></tr> </table> | Color | White | Physical state | Liquid | Flash Point | Open cup: 35°C (95°F) | Relative Density | 1.02 | Vapour Density | >1 [Air = 1] | Lower explosion limit | Lower: 1.1% | | Upper: 6.1% | Solubility | Insoluble in the following materials: cold water and hot water. | Weight | 1018.5 g/L average | Pot Life | 5-6 minutes | Dry to Sand Time | 10-15 minutes | Viscosity | 30,000 cps | Shore D Hardness | 60 to 65 (24 hr. cure) | Max. recommended Thickness (sanded) | 3 mm | Contents and Caution | MSDS Available upon request |
| Color | White | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Physical state | Liquid | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Flash Point | Open cup: 35°C (95°F) | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Relative Density | 1.02 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Vapour Density | >1 [Air = 1] | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Lower explosion limit | Lower: 1.1% | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | Upper: 6.1% | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Solubility | Insoluble in the following materials: cold water and hot water. | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Weight | 1018.5 g/L average | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Pot Life | 5-6 minutes | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Dry to Sand Time | 10-15 minutes | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Viscosity | 30,000 cps | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Shore D Hardness | 60 to 65 (24 hr. cure) | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Max. recommended Thickness (sanded) | 3 mm | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Contents and Caution | MSDS Available upon request | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |

TECHNICAL DATA SHEET

Easy Sand™ - Flowable

103235

Flowable Stopper

| | |
|-------------------------------|---|
| | <p>2004/42/IIIB(b)(250)(97) VOC IIB/b. Bodyfiller/stopper – All types. EU limit values: 250g/l. (2007) This product contains a maximum of 97 g/l VOC.</p> <hr/> <p>Properties are typical values and should not be considered as sales specifications. Physical testing performed at approximately 25°C (77°F)/ 75% RH unless otherwise noted.</p> |
| SAFETY & HANDLING: | <p>Read all directions and warnings prior to using Evercoat products. Material Safety Data Sheets can be found online at evercoat.com.</p> |