


PRODUCT: METAL GLAZE® Ultra

PART NUMBER: 100425 30 Oz. Pump 6 units/case
100424 16 Oz. Pouch 6 units/case

DESCRIPTION: METAL GLAZE® Ultra is the world's best sanding polyester putty for use as a finishing coat over body filler, large panels, or small spot filling. Its unparalleled sanding qualities are a result of the patent pending EcoResin™. Its unique thinner viscosity makes it ideally suited for intermixing with other Metalworks® products to improve flowout. Formulated with ZNX-7® for improved adhesion.

APPROVED SUBSTRATES:



- Sanded Body Filler
- Steel
- Aluminum
- Fiberglass
- E-Coat
- Silicon Bronze Welds
- Sanded OEM Paint
- Galvanized Steel
- SMC
- Stainless Steel
- Cured sanded 2K primer
- Rigid to Semi-Rigid Thermoset Plastics


NOTE: For flexible plastics, use POLY-FLEX™ Flexible Glazing Putty.

PREPARATION:



- Clean and degrease the entire panel to be repaired with soap and water, followed by a mild cleaning solvent. Thoroughly dry the surface before repairing.
- Use 80-180 grit to remove or scuff the paint and featheredge.

MIXING:



- Place the desired amount of material on a clean, non-fibrous surface. Knead the cream hardener before use.
- Measure hardener 2% by weight by adding a ribbon of cream hardener from edge to edge across the center of a 4" (10 cm) diameter puddle. Puddles larger than 4" in diameter will require additional hardener.
- Mix thoroughly until uniform color is achieved.
- Approximate setting time is 2.5 - 4.5 minutes @ 72°F (22°C)

APPLICATION:



- Spread a thin layer of mixed material over surface using firm pressure.
- Apply additional layers to build material slightly higher than the surface to allow for sanding to desired contour.

NOTE: Do not apply over new or uncured coatings. Avoid thick heavy applications.

FINISH:



- Sand to contour with 180 grit sandpaper.
- Final sand with 180 grit followed by 220-320 grit if desired.

TOPCOAT:



- Apply 2K polyester, 2K urethane, 2K epoxy, or 1K primer to manufacturer's recommendations.

TECHNICAL SPECIFICATIONS:

- | | |
|--------------------------------------|---|
| ▪ Appearance | Light Green Thixotropic Liquid |
| ▪ VOC | Refer to Section 9 of the Safety Data Sheet |
| ▪ Relative Density | Refer to Section 9 of the Safety Data Sheet |
| ▪ Sand Time | 10-15 min. |
| ▪ Max Recommended Thickness (sanded) | 1/8 inch (3mm) |

NOTE: Properties are typical values and should not be considered as sales specifications. Physical testing performed @ -72°F (22°C) / 75% RH unless otherwise noted.

SAFETY & HANDLING:

Read all directions and warnings prior to using Evercoat® products. Safety Data Sheets can be found online at evercoat.com.

NOTES:

Never return mixed filler to container

Keep can closed and store in a cool dry place

USE WITH EVERCOAT CREAM HARDENER ONLY!

EVERCOAT®

a division of Illinois Tool Works Inc. | 6600 Cornell Road | Cincinnati, OH 45242 | (513) 489-7600

©2017 Evercoat

evercoat.com

100-211-100425-TDS

7.2017