






TECHNICAL DATA SHEET

EuroSand™
Filler

104270

USES:	<p>FOR PROFESSIONAL USE ONLY</p> <p>A polyester finishing and blending putty for filling and skim coating bodywork, pinholes, grind marks, low spots, and other surface imperfections. Adheres well to steel, galvanized, other zinc coated steel, aluminum, and most rigid to semi-rigid fiberglass and thermo-set plastics.</p>																														
STORAGE:	 <p>Store in accordance with local regulations. Observe label precautions. Do not store above the following temperature: 25°C (77°F). Store in a cool, well-ventilated area away from incompatible materials and ignition sources. Keep away from: oxidizing agents, strong alkalis, strong acids. No smoking. Prevent unauthorized access. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not empty into drains. Never return mixed product back into container.</p>																														
PREPARATION:	 <p>Prior to sanding, clean the entire repair area with soap and water, followed by a mild degreasing cleaning solvent. Sand repair area, removing only the paint. Use finer grit to remove any coarse sand scratches and to featheredge the paint. Remove dust.</p>																														
MIXING:	 <p><i>Use with Cream Hardener Only!</i></p> <p>Measure hardener 2% by weight (approximately a ribbon of cream hardener from edge to edge across the center of a 10cm diameter puddle). Puddles larger than 10cm in diameter will require additional hardener. Mix thoroughly until uniform color is achieved.</p>																														
APPLICATION:	 <p>Apply in thin layers and spread smoothly. Do not apply over fresh or uncured coatings. Allow to cure fully before finishing.</p>																														
FINISHING:	 <p>Sand to knock down high spots. Avoid coarse sand scratches outside the repair area during the initial cut. Finish sand and featheredge to remove scratches.</p>																														
TECHNICAL SPECIFICATIONS:	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td>Color</td> <td>White</td> </tr> <tr> <td>Flash Point</td> <td>Open cup: 35°C (95°F)</td> </tr> <tr> <td>Relative Density</td> <td>1.02</td> </tr> <tr> <td>Vapour Density</td> <td>>1 [Air = 1]</td> </tr> <tr> <td>Lower explosion limit</td> <td>Lower: 1.1%</td> </tr> <tr> <td></td> <td>Upper: 6.1%</td> </tr> <tr> <td>Solubility</td> <td>Insoluble in the following materials: cold water and hot water.</td> </tr> <tr> <td>Weight</td> <td>1018.5 g/L average</td> </tr> <tr> <td>Pot Life</td> <td>4-6 minutes</td> </tr> <tr> <td>Dry to Sand Time</td> <td>20 minutes</td> </tr> <tr> <td>Viscosity</td> <td>200,000-250,000 cps</td> </tr> <tr> <td>Shore D Hardness</td> <td>60 to 65 (24 hr. cure)</td> </tr> <tr> <td>Max. recommended Thickness (sanded)</td> <td>3 mm</td> </tr> <tr> <td>Contents and Caution</td> <td>MSDS Available upon request</td> </tr> <tr> <td>VOC</td> <td>2004/42/II(b)(250)(38)</td> </tr> </table>	Color	White	Flash Point	Open cup: 35°C (95°F)	Relative Density	1.02	Vapour Density	>1 [Air = 1]	Lower explosion limit	Lower: 1.1%		Upper: 6.1%	Solubility	Insoluble in the following materials: cold water and hot water.	Weight	1018.5 g/L average	Pot Life	4-6 minutes	Dry to Sand Time	20 minutes	Viscosity	200,000-250,000 cps	Shore D Hardness	60 to 65 (24 hr. cure)	Max. recommended Thickness (sanded)	3 mm	Contents and Caution	MSDS Available upon request	VOC	2004/42/II(b)(250)(38)
Color	White																														
Flash Point	Open cup: 35°C (95°F)																														
Relative Density	1.02																														
Vapour Density	>1 [Air = 1]																														
Lower explosion limit	Lower: 1.1%																														
	Upper: 6.1%																														
Solubility	Insoluble in the following materials: cold water and hot water.																														
Weight	1018.5 g/L average																														
Pot Life	4-6 minutes																														
Dry to Sand Time	20 minutes																														
Viscosity	200,000-250,000 cps																														
Shore D Hardness	60 to 65 (24 hr. cure)																														
Max. recommended Thickness (sanded)	3 mm																														
Contents and Caution	MSDS Available upon request																														
VOC	2004/42/II(b)(250)(38)																														

TECHNICAL DATA SHEET

EuroSand™
Filler

104270

	<p>IIB/b. Bodyfiller/stopper – All types. EU limit values: 250g/l. (2007) This product contains a maximum of 38 g/l VOC.</p> <hr/> <p>Properties are typical values and should not be considered as sales specifications. Physical testing performed at approximately 25°C (77°F)/ 75% RH unless otherwise noted.</p> <hr/>
SAFETY & HANDLING:	<p>Read all directions and warnings prior to using Evercoat products. Material Safety Data Sheets can be found online at evercoat.com.</p>