

PRODUCT: SPOT-LITE™ PREMIUM LIGHTWEIGHT POLYESTER FINISHING AND SPOT PUTTY

PART

NUMBER:	100445	20 oz. can	12 units/case	21 lbs/case
	100446	30 oz. Pump-tainer	4 units/case	18 lbs/case

DESCRIPTION: SPOT-LITE™ is a paste putty that levels like a pourable putty. Contains Hattonite™ for improved sandability. Cures quickly to a sandable state which makes it the ideal product for quick spot filling. Stain resistant for use under basecoat/clearcoat repairs. May be applied to galvanized metal, aluminum, bare steel, body filler, two part primers and sanded OEM finishes. Part of the METALWORKS® System. Blue cream hardener included.

FEATURES & BENEFITS:

Cream-like consistency for improved spreading with no sag.

Lightweight; cuts faster when sanded.

Contains Hattonite™, an ingredient which lubricates sandpaper, reducing heat and friction for easier sanding.

Fast drying formula ideally suited for quick spot repair.

METALWORKS® product with ZNX-7™ to provide excellent adhesion and featheredging to galvanized steel and aluminum.

Offers a corrosion warranty that honors the OEM warranty.

USES: Use as a finish coat over body filler repair areas to fill minor defects, deep sand scratches and pinholes prior to applying primer surfacer to improve the efficiency of the primer coat. Can also be used to fill minor body damage up to 1/8" in depth.

APPROVED

SUBSTRATES: Steel, Galvanized and other zinc coated steel, and most rigid to semi-rigid fiberglass and thermo-set plastics. For flexible plastics, use POLY-FLEX™ Flexible Polyester Glazing Putty.

PREPARATION: Clean surface. Remove all dirt, oil grease and wax. Use an 80—180 grit disc to remove or scuff paint. Surface must be completely dry before application.

MIXING: Place desired amount of putty on a clean, non-fibrous mixing board. Add a ribbon of cream hardener from edge to edge across the center of dispensed putty. Puddles larger than 4" in diameter will require additional hardener. Mix thoroughly until uniform color is achieved. Approximate setting time is 5-6 minutes @ 75° to 80°F (27°C).

APPLICATION: Spread a thin layer of mixed material over surface using firm pressure to ensure best adhesion. Apply additional layers building area slightly higher than the surface to allow for sanding. Do not apply over fresh or uncured coatings.

FINISH: Sandable in approximately 20 minutes. Sand hardened putty with 180-220 grit sandpaper followed by 320 grit if desired.

SPOT-LITE

PAGE 2

TECHNICAL SPECIFICATIONS:

Appearance	Light Green Thixotropic Cream
VOC	Packaged: 1.50 lbs/gal or 180 g/L
	Applied: .50 lbs/gal or 60 g/L
Weight per Gallon	8.5 lbs/gal
Gel Time	5-6 minutes
Sand Time	10-15 minutes
Viscosity	200,000 cps T-B @ 2.5 rpm
Contents and Caution	MSDS Available upon request
Crystalline Silica Content	Contains Crystalline Silica

NOTE: Properties are typical values and should not be considered as sales specifications. Physical testing performed @ ~77°F (25°C) / 75% RH unless otherwise noted.

SAFETY & HANDLING:

Read all directions and warnings prior to using Evercoat® products. Material Safety Data Sheets can be found online at www.evercoat.com.

NOTES:

Never return mixed filler to can

Keep can closed and store in a cool dry place

USE WITH CREAM HARDENER ONLY!

ZNX-7™ patent #5,456,947



Fibre Glass-Evercoat
a division of Illinois Tool Works Inc.
6600 Cornell Road • Cincinnati, OH 45242
(513) 489-7600 Fax (513)489-9229
www.evercoat.com
Made and Printed in the USA
© 2003 Fibre Glass-Evercoat