






TECHNICAL DATA SHEET

Quantum™

104108

10:1 Fine Finishing Stopper

DESCRIPTION:	Quality resins and enhanced performance characteristics are used to create this stain-free, tack-free, easy mixing, and easy sanding stopper.																								
USES:	FOR PROFESSIONAL USE ONLY Best sanding stopper! Quantum's patent-pending hybrid polyester/epoxy technology and 10:1 mix ratio make it the ultimate in today's technologically advanced stoppers. It offers superior adhesion to bare steel, galvanized, and other zinc coated steel, SMC, fiberglass, and aluminum while being extremely easy to sand without risk of pulling back the featheredge. Use with Quantum 10:1 Hardener only!																								
STORAGE:	 <p>Store in accordance with local regulations. Observe label precautions. Do not store above the following temperature: 25°C (77°F). Store in a cool, well-ventilated area away from incompatible materials and ignition sources. Keep away from: oxidizing agents, strong alkalis, strong acids. No smoking. Prevent unauthorized access. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not empty into drains. Never return mixed product back into container.</p>																								
PREPARATION:	 <p>Prior to sanding, clean the entire repair area with soap and water, followed by a mild degreasing cleaning solvent. Sand repair area, removing only the paint. Use finer grit to remove any coarse sand scratches and to featheredge the paint. Remove dust.</p>																								
MIXING:	 <p><i>Use with Quantum 10:1 Hardener Only!</i> Measure hardener 10% by volume (approximately a ribbon of Quantum 10:1 Hardener from edge to edge across the center of a 10cm diameter puddle). Puddles larger than 10cm in diameter will require additional hardener. Mix thoroughly until uniform color is achieved.</p>																								
APPLICATION:	 <p>Apply in thin layers and spread smoothly. Allow to cure fully before finishing.</p>																								
FINISHING:	 <p>Sand to knock down high spots. Avoid coarse sand scratches outside the repair area during the initial cut. Finish sand and featheredge to remove scratches.</p>																								
TECHNICAL SPECIFICATIONS:	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%;">Color</td> <td>Brown</td> </tr> <tr> <td>Physical state</td> <td>Liquid</td> </tr> <tr> <td>Flash Point</td> <td>Open cup: 34°C (93.2°F)</td> </tr> <tr> <td>pH</td> <td>7</td> </tr> <tr> <td>Relative Density</td> <td>1.15</td> </tr> <tr> <td>Vapour Density</td> <td>>1 [Air = 1]</td> </tr> <tr> <td>Lower explosion limit</td> <td>Lower: 1.1%</td> </tr> <tr> <td></td> <td>Upper: 6.1%</td> </tr> <tr> <td>Solubility</td> <td>Insoluble in the following materials: cold water and hot water.</td> </tr> <tr> <td>Weight</td> <td>1157.5 g/L average</td> </tr> <tr> <td>Pot Life</td> <td>2-3 minutes</td> </tr> <tr> <td>Dry to Sand Time</td> <td>10-15 minutes</td> </tr> </table>	Color	Brown	Physical state	Liquid	Flash Point	Open cup: 34°C (93.2°F)	pH	7	Relative Density	1.15	Vapour Density	>1 [Air = 1]	Lower explosion limit	Lower: 1.1%		Upper: 6.1%	Solubility	Insoluble in the following materials: cold water and hot water.	Weight	1157.5 g/L average	Pot Life	2-3 minutes	Dry to Sand Time	10-15 minutes
Color	Brown																								
Physical state	Liquid																								
Flash Point	Open cup: 34°C (93.2°F)																								
pH	7																								
Relative Density	1.15																								
Vapour Density	>1 [Air = 1]																								
Lower explosion limit	Lower: 1.1%																								
	Upper: 6.1%																								
Solubility	Insoluble in the following materials: cold water and hot water.																								
Weight	1157.5 g/L average																								
Pot Life	2-3 minutes																								
Dry to Sand Time	10-15 minutes																								

TECHNICAL DATA SHEET

Quantum™

10:1 Fine Finishing Stopper

104108

	Shore D Hardness	55 to 60 (24 hr. cure)
	Corrosion Resistance	500 hours Harsaw salt Spray Cabinet 200 hours at 100% RH
	Water Resistance	No blistering, wrinkling or softening after 24 hours immersion in water.
	Max. recommended Thickness (sanded)	6.3 mm
	Contents and Caution	MSDS Available upon request
	VOC	2004/42/IIIB(b)(250)(93) IIB/b. Bodyfiller/stopper – All types. EU limit values: 250g/l. (2007) This product contains a maximum of 93 g/l VOC.
	Properties are typical values and should not be considered as sales specifications. Physical testing performed at approximately 25°C (77°F)/ 75% RH unless otherwise noted.	
SAFETY & HANDLING:	Read all directions and warnings prior to using Evercoat products. Material Safety Data Sheets can be found online at evercoat.com.	