

PRODUCT: EZ Lite Commercial

PART NUMBER: 100287 **Gallon** **4 units/case**

DESCRIPTION: **EZ Lite Commercial** is specially formulated to allow for a deep filling with excellent vertical hang with a 7 – 9 minute working time at 72°F (22°C). Technicians can mix and spread large quantities with confidence knowing they have enough time to work larger surfaces. This reduces the number of mixes, saving time and increasing productivity. Evercoat Blue cream hardener included.

APPROVED SUBSTRATES:



- Steel
- Galvanized Steel
- Aluminum
- Fiberglass
- Stainless Steel
- SMC


NOTE: For structural repairs prone to high degrees of stress and flexibility, use a fiber reinforced filler such as Everglass®, Kitty Hair® or Fiber Tech®.

PREPARATION:



- Clean and degrease the entire panel to be repaired with soap and water, followed by a mild cleaning solvent. Thoroughly dry the surface before repairing.
- Keep the repair area small. Use 80 grit to remove the paint and featheredge with 180.

MIXING:



- Stir the filler before using. Knead the cream hardener.
- Measure hardener 2% by weight (add a ribbon of cream hardener from edge to edge across the center of a 4" diameter puddle).
- Puddles larger than 4" (10 cm) in diameter will require additional hardener. Mix thoroughly until uniform color is achieved.

NOTE: May be mixed with Evercoat Rage Ultra Xtra Ultra to extend working time.

APPLICATION:



- Apply in layers with even firm pressure.
- Do not apply all at once.

FINISH:



- Sand with 80-180 grit sandpaper.
- If necessary, reapply to fill any pinholes or low spots, allow filler to dry and then sand with 180 grit sandpaper.
- Finish sand with 180 grit or finer.

For optimal performance use [Evercoat Optex™ Superbuild 4:1 Hybrid Polyester Primer Surfacer](#)

TECHNICAL SPECIFICATIONS:

- | | |
|--------------------------------------|---|
| ▪ Appearance | Off White Paste |
| ▪ VOC | Refer to Section 9 of the Safety Data Sheet |
| ▪ Relative Density | Refer to Section 9 of the Safety Data Sheet |
| ▪ Work Time | 7 - 9 minutes @ 72°F (22°C) |
| ▪ Sand Time | 25 – 30 minutes |
| ▪ Max Recommended Thickness (sanded) | 1/4 inch (6mm) |

NOTE:

Properties are typical values and should not be considered as sales specifications. Physical testing performed @ ~72°F (22°C) / 75% RH unless otherwise noted.

SAFETY & HANDLING:

Read all directions and warnings prior to using Evercoat® products. Safety Data Sheets can be found online at evercoat.com.

NOTES:

Never return mixed filler to can

Keep can closed and store in a cool dry place

USE WITH EVERCOAT CREAM HARDENER ONLY!