

**PRODUCT:** 2K Primer Surfacer

**PART NUMBER:** 102505      Gallon      4 units/case      24 lbs/case

**DESCRIPTION:** **2K Primer Surfacer** is a two-component, high-solids primer surfacer that has excellent filling characteristics. It provides excellent adhesion and gloss / color holdout. 2K Primer Surfacer sands easily without clogging the sandpaper, while providing excellent resistance to sand scratch swelling.

**SUBSTRATES:**



- Treated Steel
- Treated Aluminum
- Fiberglass/SMC
- OEM Finishes
- Refinish Lacquers, Enamels and Urethanes
- Self-Etch Primers
- Body Filler/Putty


**NOTE:** Steel and Aluminum must be properly treated with an Etch Primer or Metal Etch.

**CLEANING:**



- Surface must be clean and free of dirt, oil, grease and wax
- To solvent clean **raw, exposed fiberglass**, it is recommended to clean exposed area with **acetone**.


**MIXING:**



**4 Parts**      **1 Part**  
#2505      to      #2507  
2K Primer Surfacer      2K Primer Catalyst

- Shake and stir the primer and catalyst thoroughly before mixing

**POTLIFE:**



1 hour @ 70°F (21°C)  
45 min. @ 80°F (27°C)  
30 min. @ 90°F (32°C)

- Clean spray gun immediately after use

**APPLICATION:**



- Use a primer gun with a 1.4 to 1.8 fluid nozzle/air cap at a recommended air pressure of 5-7 psi at the cap
- Apply **2-3** medium wet coats allowing **3-5** minutes flash time between coats

### DRYING:



- Air Dry: 1.5 – 3 hours @ 70°F (21°C)
- Force Dry: 30 min. @ 140°F (60°C)
- Dry-to-Sand: 2 hours air dry; upon cool down for force dry.

**NOTE:** Dry times may vary based on film build and ambient air temperature.

### FINISH:



- Initial Sand: 180 – 320 grit
- Final Sand to Seal: 400 grit
- Final Sand to Topcoat: 600 grit

### TECHNICAL SPECIFICATIONS:

Appearance	Gray liquid
VOC	Refer to Section 9 of the Safety Data Sheet
Recommended Dry-Film-Thickness (DFT) after Sanding	2.0 – 2.5 mils
Maximum DFT after Sanding	6.0 mils

### SAFETY & HANDLING:

**IMPORTANT:** The contents of these packages must be mixed with other components before the products can be used. Before opening the packages, be sure to understand the warnings on all labels of all components since the resulting product will have the warnings and cautions of all its parts. Improper spray technique may result in hazardous conditions. Follow the spray equipment manufacturer's instructions to prevent injury or fire. Follow respirator manufacturer's directions for respirator use. Always wear eye and skin protection. Observe all precautions. Consult MSDS for further safety information and/or handling instructions. In case of emergency, contact your local emergency room or poison control center immediately. **For professional use only.**