

PRODUCT: Edge Premium Putty

PART

NUMBER:	200540	16 Oz. Pouch	6 units/case	8 lbs/case
	200545	30 Oz. Pump	6 units/case	14 lbs/case

DESCRIPTION: Edge Premium Putty is the world's best sanding polyester putty for use as a finishing coat over body filler, large panels, or small spot filling. Its unparalleled sanding qualities are a result of the patent pending EcoResin™. Its unique thinner viscosity makes it ideally suited for intermixing with other Metalworks® products to improve flowout. Formulated with ZNX-7® for improved adhesion.

APPROVED SUBSTRATES:



- Sanded Body filler
- Steel
- Galvanized Steel
- E-Coat
- Aluminum
- Rigid to Semi-rigid Thermoset Plastics
- SMC
- Fiberglass (cosmetic repairs only)
- Cured sanded 2K primer surfacers
- Sanded OEM paint


NOTE: For flexible plastics, use POLY-FLEX™ Flexible Glazing Putty.

PREPARATION:



- Clean and degrease the entire panel to be repaired with soap and water, followed by a mild cleaning solvent. Thoroughly dry the surface before repairing.
- Use 80-180 grit to remove or scuff the paint and featheredge.

MIXING:



- Place the desired amount of material on a clean, non-fibrous surface. Knead the cream hardener before use.
- Measure hardener 2% by weight (add a ribbon of cream hardener from edge to edge across the center of a 4" (10 cm) diameter puddle. Puddles larger than 4" in diameter will require additional hardener.
- Mix thoroughly until uniform color is achieved.

APPLICATION:



- Spread a thin layer of mixed material over surface using firm pressure.
 - Apply additional layers to build material slightly higher than the surface to allow for sanding to desired contour
- NOTE:** Do not apply over new or uncured coatings. Avoid thick heavy applications.

FINISH:



- Sand to contour with 180 grit sandpaper.
- Final sand with 180 grit followed by 220-320 grit if desired.

TOPCOAT:



- Allow 45-60 minutes to apply 2K polyester, 2K urethane, 2K epoxy, or 1K primer.
- Follow manufacturer's recommendations.

TECHNICAL SPECIFICATIONS:

- | | |
|------------------------|---|
| ▪ Appearance | Light Green Thixotropic Liquid |
| ▪ VOC | Refer to Section 9 of the Safety Data Sheet |
| ▪ Gel Time | 2.5 - 4.5 minutes |
| ▪ Sand Time | 10 - 15 minutes |
| ▪ Corrosion Resistance | 500 hrs (ASTM B117) |
| ▪ Max Rec. Thickness | 1/8 inch (3mm) |
| ▪ Max allowable heat | 260°F (126.6°C) Surface Temp |

NOTE: Properties are typical values and should not be considered as sales specifications. Physical testing performed @ ~72°F (22°C) / 75% RH unless otherwise noted.

SAFETY & HANDLING:

Read all directions and warnings prior to using Evercoat® products. Material Safety Data Sheets can be found online at www.theevercoatedge.com.

NOTES:

Never return catalyzed material to container

Keep container closed and store in a cool dry place

USE WITH EVERCOAT CREAM HARDENER ONLY!