


PRODUCT: GLAZE COAT Polyester Putty

PART NUMBER: 100417 30 Oz. Pump 6 units/case
Packaged with White Cream Hardener

DESCRIPTION: **GLAZE COAT** was the first pourable finishing putty in the market. Like METAL GLAZE®, GLAZE COAT is vacuum processed for reduced pinholes and offers the same Features, Benefits and Performance as METAL GLAZE®, in a BUFF colored formula. Part of the Metal Works® System. White cream hardener included.

APPROVED SUBSTRATES:



- Steel
- Fiberglass
- Aluminum
- Sanded Body Filler
- Galvanized Steel
- Most Rigid to Semi-Rigid Plastics
- Cured Sanded OEM Finishes
- Cured Sanded 2K Primer Surfacer


NOTE: For flexible plastics, use POLY-FLEX™ Flexible Glazing Putty.

PREPARATION:



- Clean and degrease the entire panel to be repaired with soap and water, followed by a mild cleaning solvent. Thoroughly dry the surface before repairing.
- Use 80-180 grit to remove or scuff the paint and featheredge.

MIXING:



- Place the desired amount of material on a clean, non-fibrous surface. Knead the cream hardener before use.
- Measure hardener 2% by weight (add a ribbon of cream hardener from edge to edge across the center of a 4" (10 cm) diameter puddle. Puddles larger than 4" in diameter will require additional hardener.
- Mix thoroughly until uniform color is achieved.
- Approximate setting time is 4 - 5 minutes @ 72°F (22°C)

APPLICATION:



- Spread a thin layer of mixed material over surface using firm pressure.
- Apply additional layers to build material slightly higher than the surface to allow for sanding to desired contour

NOTE: Do not apply over new or uncured coatings. Avoid thick heavy applications.

FINISH:



- Sand to contour with 180 grit sandpaper.
- Final sand with 180 grit followed by 220-320 grit if desired.

TOPCOAT:



- Apply 2K polyester, 2K urethane, 2K epoxy, or 1K primer to manufacturer's recommendations

TECHNICAL SPECIFICATIONS:

▪ Appearance	Light Yellow Colored Thixotropic Liquid
▪ VOC	Refer to Section 9 of the Safety Data Sheet
▪ Relative Density	Refer to Section 9 of the Safety Data Sheet
▪ Setting Time	4-5 min.
▪ Sand Time	25-30 min.
▪ Max Recommended Thickness (sanded)	1/8 inch (3mm)

NOTE: Properties are typical values and should not be considered as sales specifications. Physical testing performed @ -72°F (22°C) / 75% RH unless otherwise noted.

SAFETY & HANDLING:

Read all directions and warnings prior to using Evercoat® products. Safety Data Sheets can be found online at evercoat.com.

NOTES:

Never return mixed filler to container

Keep can closed and store in a cool dry place

USE WITH CREAM HARDENER ONLY!