


**PRODUCT:** METAL GLAZE® Ultra

**PART NUMBER:** 100425      30 Oz. Pump      6 units/case

**DESCRIPTION:** METAL GLAZE® Ultra is the world's best sanding polyester putty for use as a finishing coat over body filler, large panels, or small spot filling. Its unparalleled sanding qualities are a result of EcoResin™. Its unique thinner viscosity makes it ideally suited for intermixing with other Metalworks® products to improve flow out. Formulated for improved adhesion.

**Meets 500-hour corrosion resistance (ASTM B117)**

**APPROVED SUBSTRATES:**



- Sanded Body Filler
- Steel
- Aluminum
- Fiberglass
- E-Coat
- Silicon Bronze Welds
- Sanded OEM Paint
- Galvanized Steel
- SMC
- Stainless Steel
- Cured sanded 2K primer
- Rigid to Semi-Rigid Thermoset Plastics


**NOTE:** For flexible plastics, use POLY-FLEX™ Flexible Glazing Putty.

**PREPARATION:**



- Clean and degrease the entire panel to be repaired with soap and water, followed by a mild cleaning solvent. Thoroughly dry the surface before repairing.
- Use 80-180 grit to remove or scuff the paint and featheredge.

**MIXING:**



- Place the desired amount of material on a clean, non-fibrous surface. Knead the cream hardener before use.
- Measure hardener 2% by weight by adding a ribbon of cream hardener from edge to edge across the center of a 4" (10 cm) diameter puddle. Puddles larger than 4" in diameter will require additional hardener.
- Mix thoroughly until uniform color is achieved.
- Approximate setting time is 2.5 - 4.5 minutes @ 72°F (22°C)

### APPLICATION:



- Spread a thin layer of mixed material over surface using firm pressure.
- Apply additional layers to build material slightly higher than the surface to allow for sanding to desired contour.

**NOTE:** Do not apply over new or uncured coatings. Avoid thick heavy applications.

### FINISH:



- Sand to contour with 180 grit sandpaper.
- Final sand with 180 grit followed by 220-320 grit if desired.

### TOPCOAT:



- Apply 2K polyester, 2K urethane, 2K epoxy, or 1K primer to manufacturer's recommendations.

### TECHNICAL SPECIFICATIONS:

• Appearance	Light Green Thixotropic Liquid
• VOC	Refer to Section 9 of the Safety Data Sheet
• Relative Density	Refer to Section 9 of the Safety Data Sheet
• Setting Time	2.5 - 4.5 min.
• Sand Time	10 - 15 min.
• Max Recommended Thickness (sanded)	1/8 inch (3mm)

**NOTE:** Properties are typical values and should not be considered as sales specifications. Physical testing performed @ -72°F (22°C) / 75% RH unless otherwise noted.

### SAFETY & HANDLING:

Read all directions and warnings prior to using Evercoat® products. Safety Data Sheets can be found online at evercoat.com.

### NOTES:

Never return mixed filler to container

Keep can closed and store in a cool dry place

**USE WITH EVERCOAT CREAM HARDENER ONLY!**



a division of Illinois Tool Works Inc. | 6600 Cornell Road | Cincinnati, OH 45242 | (513) 489-7600

©2024 Evercoat

[evercoat.com](http://evercoat.com)

100-211-100425-TDS

4.2024