

PRODUCT: Z-GRIP® LUXE Lightweight Filler

PN: 100483 **Gallon** **4 units/case**

DESCRIPTION: Z-GRIP® LUXE Lightweight Filler is a golden, creamy, and super spreadable filler that moves with low resistance, bringing control to the application from the first pass. This advanced formula filler delivers a reined, wet look and stays smooth across the panel.

FEATURES: Superior Sanding
Superior Spreadability & Smooth Finish
Superior Pinhole Resistance
Superior Adhesion to Most Substrates (Including Galvanized Steel)

SUBSTRATES: Steel, Galvanized Steel, Aluminum, Fiberglass and SMC




NOTE: For structural repairs prone to high degrees of stress and flexibility, use a fiber reinforced filler such as Everglass®, Kitty Hair® or Fiber Tech®.

PREPARATION:



- Clean and degrease the entire panel to be repaired with soap and water, followed by a mild cleaning solvent. Surface must be thoroughly dry before repairing or applying material. Surface must be clean and free of dirt, oil, grease and wax.
- Keep the repair area small. Use 80 grit to remove the paint and featheredge.

MIXING:



- Stir the filler before using. Knead the cream hardener
- Measure hardener 2% by weight (add a ribbon of cream hardener from edge to edge across the center of a 4" diameter puddle).
- Puddles larger than 4" (10 cm) in diameter will require additional hardener. Mix thoroughly until uniform color is achieved.
- Approximate setting time is 5-6 minutes @ 72°F (22°C)

APPLICATION:



- Apply in layers with even firm pressure.
- Do not apply all at once.

FINISH:



- Sand filler with 80 grit or finer
- Final sand repair and paint edge 180 grit or finer

For best results, apply a premium Evercoat putty to provide a smoother finish and reduce the amount of primer surfacer needed for a quality finish.

TECHNICAL SPECIFICATIONS:

- | | |
|---|---|
| • Appearance | Gold Colored Paste |
| • VOC | Refer to Section 9 of the Safety Data Sheet |
| • Relative Density | Refer to Section 9 of the Safety Data Sheet |
| • Sand Time | 15-20 minutes |
| • Max Recommended Thickness (After Sanding) | ¼ inch (6 mm) |

Properties are typical values and should not be considered as sales specifications. Physical testing performed @ ~72°F (22°C) / 75% RH unless otherwise noted.

NOTES:

Never return mixed filler to can

Keep can closed and store in a cool dry place

USE WITH CREAM HARDENER ONLY!

SAFETY & HANDLING:

Read full instructions before use. This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Safety Data Sheets (SDS) and warnings displayed on product labels must be read carefully. SDS and product labels convey the possible health hazards, appropriate engineering controls, personal protection equipment and precautions to be observed in using the material. Copies of the SDS and product labels are available upon request. Consult your local environmental compliance agency for the disposal of un-used products. Never dispose of products down the drain. If exposed, contact a POISON CONTROL CENTER IMMEDIATELY. KEEP OUT OF REACH OF CHILDREN. The information provided in this Technical Data Sheet is correct to the best of our knowledge, information and belief at the date of its publication.