

PRODUCT: MXM™ SLOW PREMIUM 2K EPOXY PLASTIC REPAIR

PN: 100898 280 mL Cartridge 6 units/case

DESCRIPTION: MXM™ SLOW PREMIUM 2K EPOXY PLASTIC REPAIR is a two-component epoxy formulated for speed, superior strength, and excellent sandability. This fast-setting epoxy streamlines the plastic repair process by eliminating the need to identify the substrate or apply an adhesion promoter. Multi-Fix is ideal for repairing tears, nicks, gouges, and a variety of quick-fix applications across a wide range of plastic parts. Can also be applied over MXM™ #886 Super Fast and MXM™ #887 Fast Urethane Adhesives as a finishing material

FEATURES:

- 1:1 mix ratio
- Excellent filling
- Easy Sanding
- Remains flexible after cure
- Packaged in a Universal Cartridge
- Applied with a professional grade caulking gun

SUBSTRATES: PP, TPO, PUR, RIM, RRIM, FRP, SMC, and other automotive plastics

PREPARATION: Surface must be clean and free of dirt, oil, grease and wax. Clean the area with soap and water, followed by an all-purpose solvent cleaner. Use a clean, dry cloth to wipe the area dry. Sand the area with 80-180 grit. Remove the sanding dust with clean compressed air. For Olefin-based plastics such as TPO, PP and PP+ blended plastics an adhesion promoter can be used for optimum performance. For cosmetic corrections apply a second coat and re-sand as needed.

APPLICATION: Equalize the cartridge until both parts flow equally. Install the included mix tip. Dispense initial material equal to the length of the mix tip to ensure proper mix. Apply to the repair area with steady pressure to the caulking gun during application. Allow to dry, then sand 80-180 grit. Apply primer surfacer according to coating manufacturer recommendations. Heat will reduce the working time. Cooler temperatures will lengthen the time. For maximum shelf life store at 75°F (24°C) or below.

TECHNICAL SPECIFICATIONS:

- Appearance Black / Opaque
- VOC Refer to Section 9 of the Safety Data Sheet
- Odor Amine / Mercaptan
- Working Time 4-6 minutes
- Sanding Time 20-30 minutes
- Cure Time 4 hours @ 72° F (22°C)

NOTE: Properties are typical values and should not be considered as sales specifications. Physical testing performed @ ~72°F (22°C) / 75% RH unless otherwise noted.

SAFETY & HANDLING:

For Professional use only. Read all directions and warnings prior to using Evercoat® products. Keep cartridge closed and store in a cool dry place.

SAFETY & HANDLING:

Read full instructions before use. This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Safety Data Sheets (SDS) and warnings displayed on product labels must be read carefully. SDS and product labels convey the possible health hazards, appropriate engineering controls, personal protection equipment and precautions to be observed in using the material. Copies of the SDS and product labels are available upon request. Consult your local environmental compliance agency for the disposal of un-used products. Never dispose of products down the drain. If exposed, contact a POISON CONTROL CENTER IMMEDIATELY. KEEP OUT OF REACH OF CHILDREN. The information provided in this Technical Data Sheet is correct to the best of our knowledge, information and belief at the date of its publication.



a division of Illinois Tool Works Inc. | 6600 Cornell Road | Cincinnati, OH 45242 | (513) 489-7600

©2026 Evercoat

evercoat.com

100-310-100887-TDS
3.2026