


PRODUCT: Z-GRIP LUXE Putty

PN: 100488 24 oz. Pouch 6 units/case

DESCRIPTION: Evercoat® Z-Grip Luxe Putty is a premium finishing putty designed to eliminate pinholes, scratches, and minor surface imperfections before priming. Its ultra-smooth, creamy formula provides exceptional spreadability, easy application, and fast sanding for improved productivity. Packaged in a convenient pouch, Z-Grip Luxe Putty offers better dispensing control, reduced waste, and more efficient product use, helping technicians achieve a flawless surface faster.

FEATURES: Available in a pouch for dispensing control
Ultra smooth finish
Broad Substrate Compatibility

SUBSTRATES: Steel, Galvanized Steel, Aluminum, Fiberglass, Sanded Body Filler, Most Rigid to Semi-Rigid Plastics, Cured sanded OEM Finishes and cured sanded 2K Primer Surfacers




NOTE: For flexible plastics, use POLY-FLEX™ Flexible Glazing Putty.

PREPARATION:



- Clean and degrease the entire panel to be repaired with soap and water, followed by a mild cleaning solvent. Surface must be thoroughly dry before repairing or applying material.
- Use 80-180 grit to remove or scuff the paint and featheredge.

MIXING:



- Place the desired amount of material on a clean, non-fibrous surface. Knead the cream hardener before use.
- Measure hardener 2% by weight (add a ribbon of cream hardener from edge to edge across the center of a 4" (10 cm) diameter puddle. Puddles larger than 4" in diameter will require additional hardener.
- Mix thoroughly until uniform color is achieved.

APPLICATION:



- Spread a thin layer of mixed material over surface using firm pressure.
- Apply additional layers to build material slightly higher than the surface to allow for sanding to desired contour

NOTE: Do not apply over new or uncured coatings. Avoid thick heavy applications.

FINISH:



- Shape with 180 grit sandpaper
- Final sand repair with 180 grit followed by 220 – 320 grit if desired.

TOPCOAT:



- Apply 2K polyester, 2K urethane, 2K epoxy, or 1K primer to manufacturer's recommendations

TECHNICAL SPECIFICATIONS:

- | | |
|--------------------------------------|---|
| • Appearance | Light Yellow Colored Paste |
| • VOC | Refer to Section 9 of the Safety Data Sheet |
| • Relative Density | Refer to Section 9 of the Safety Data Sheet |
| • Work Time | 4 - 5 minutes @ 72°F (22°C) |
| • Sand Time | 18 - 20 minutes @ 72°F (22°C) |
| • Max Recommended Thickness (sanded) | 1/8 inch (3 mm) |

Properties are typical values and should not be considered as sales specifications.

Physical testing performed @ ~72°F (22°C) / 75% RH unless otherwise noted.

NOTES:

Never return mixed filler to can

Keep can closed and store in a cool dry place

USE WITH EVERCOAT CREAM HARDENER ONLY!

SAFETY & HANDLING:

Read full instructions before use. This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Safety Data Sheets (SDS) and warnings displayed on product labels must be read carefully. SDS and product labels convey the possible health hazards, appropriate engineering controls, personal protection equipment and precautions to be observed in using the material. Copies of the SDS and product labels are available upon request. Consult your local environmental compliance agency for the disposal of un-used products. Never dispose of products down the drain. If exposed, contact a POISON CONTROL CENTER IMMEDIATELY. KEEP OUT OF REACH OF CHILDREN. The information provided in this Technical Data Sheet is correct to the best of our knowledge, information and belief at the date of its publication.